

FLOOR FINISH



Classic™

TWENTY-FIVE

WET LOOK GLOSS, DURABLE, ULTRA HIGH SPEED FLOOR FINISH FOR HIGH TRAFFIC AREAS ON RESILIENT AND HARD FLOORS

PRODUCT SPECIFICATION BULLETIN

THE FINEST IN JANITORIAL PRODUCTS, SUPPLIES AND EQUIPMENT SINCE 1946

Product No. 108

PRODUCT DESCRIPTION

Date revised 9/2004

LAWTON'S CLASSIC TWENTY-FIVE represents the ultimate in a high solids floor finish. A versatile easy to apply floor finish that holds up to heavy traffic, detergent scrubbing and ultra-high speed burnishing. CLASSIC TWENTY-FIVE is the ideal choice for low maintenance programs as well.



CLASSIFIED BY UNDERWRITER'S LABORATORIES, INC.® AS TO SLIP RESISTANCE ONLY. 59X9

DIRECTIONS

- **FLOOR PREPARATION:** Remove old seals and finishes with LAWTON'S BLAST OFF – use as directed. Neutralize floor with LAWTON'S FLOOR CONDITIONER – use as directed. Rinse floor well with clean water and allow to thoroughly dry. Seal floor with LAWTON'S CLASSIC SEAL (optional). Apply 1 or 2 coats of seal as directed.
- **APPLICATION:** Apply 2 to 4 coats of LAWTON'S CLASSIC FINISH, using a clean finish mop, allowing 30 to 60 minutes dry time between coats. For best results, apply thin even coats with 30 minutes dry time between coats.
- **MAINTENANCE:** (1) Dust mop daily with treated dust mop. (2) Damp mop or auto mop daily with LAWTON'S N-L-C. (3) Burnish with LAWTON'S UHS floor pad on a 1500-3000 rpm burnisher. (4) As needed, apply LAWTON'S UHS CLASSIC RESTORER using mop on method as directed.
- **FUTURE CARE:** When burnishing no longer restores gloss, scrub floor with LAWTON'S N-L-C, rinse thoroughly and apply 2 coats of CLASSIC FLOOR FINISH.

CAUTIONS

CAUTION: Keep out of reach of children. Any liquids spilled on a finished floor will cause a hazardous, slippery condition. Clean up of spills should have immediate attention. Avoid eye contact. For eye contact, rinse with water. If irritation persists, get medical help. Do not swallow. If swallowed get medical help immediately.

WARNING: Do not pour unused finish back into container as it will damage the product.

CAUCIÓN: Mantenga fuera del alcance de los niños. Cualquier líquido derramado en un piso acabado causará una condición peligrosa deslizada. Cualquier derramamiento debe recibir atención inmediata. Evite el contacto con los ojos. En caso de que hay contacto con los ojos, enjuague inmediatamente con agua. Si persiste la irritación, busque asistencia médica. Este producto no es para beber. Si se traga, busque asistencia médica inmediatamente.

AVISO: No vacie el restante del acabado nuevamente dentro del envase pues dañará el producto.

HAZARDOUS INGREDIENTS:

Diethyleneglycolmonoethylether.....	CAS No. 111-90-0
Dipropyleneglycolmonomethylether.....	CAS No. 34590-94-8
2,2,4-Trimethyl-1,3-pentanediolmonoisobutyrate.....	CAS No. 25265-77-4
Tributoxyethylphosphate.....	CAS No. 78-51-3

PROTECTIVE EQUIPMENT

It is recommended to wear protective gloves and protective eyewear when using this or any chemical cleaning product. When spray applying, ventilation and breathing protection is recommended.

TECHNICAL DATA

Nonvolatile solids.....	24.0 ± 1% by wt.
Color and appearance.....	Milk white liquid.
Odor.....	Mild ammonia odor.
Viscosity.....	Water thin.
pH.....	9.0 ± .5 @ 25°C.
Specific Gravity.....	1.034 @ 25°C.
Weight per gallon.....	8.59 lbs. per gallon.
Dry time, (thin coat) standard humidity.....	10 min.
Dry time (average coat).....	15-20 min.
Cure time to re-coat (thin coat).....	30 min.
Cure time to re-coat (average coat).....	30-60 min.
Leveling.....	Excellent.
Gloss.....	Excellent.
Black heel mark resistance.....	Excellent.
Detergent resistance.....	Excellent.
Removability.....	Yes with good high-end strippers.
Slip resistance.....	Passes .5 on James machine.
Nonyellowing.....	Good.
Dry film clarity.....	Excellent.
Freeze / thaw stability.....	Passes standard.
V.O.C. (Volatile Organic Content).....	7.0% by wt.
Flash point.....	Nonflammable.
Shelf life (stored properly).....	1 year.

READY TO USE

LAWTON BROS., INC. MANUFACTURING CHEMISTS

ORLANDO

2515 DINNEEN AVENUE
P.O. BOX 547635
ORLANDO, FL 32854-7635
PH: 407-291-2501 ● 800-432-0813
FAX: 407-290-0471

CLEARWATER BRANCH

14420 - 60TH STREET NORTH
CLEARWATER, FL 33760
PH: 727-531-1179 ● 800-328-3210
FAX: 727-531-4566

OCALA BRANCH

1507 SOUTH PINE AVENUE
OCALA, FL 34474
PH: 352-629-8810 ● 800-421-5777
FAX: 352-629-3797

MELBOURNE BRANCH

114 SOUTH BABCOCK STREET
MELBOURNE, FL 32901
PH: 321-951-0861
FAX: 321-951-9210